

Anbefalt turtall ved bruk av HSS bor

mm Zoll / inch		500N/mm ² Steel ≤ 500N/mm ²	750N/mm ² Steel ≤ 750N/mm ²	900N/mm ² Steel ≤ 900N/mm ²	1200N/mm ² Steel ≤ 1200N/mm ²	1400N/mm ² Steel ≤ 1400N/mm ²	Stainless steel	Aluminum	Cast iron	Cast copper
12	7/16"	663	530	344	265	185	318	981	477	1061
13	17/32"	612	489	318	244	171	293	905	440	979
14	19/32"	568	454	295	227	159	272	841	409	909
15	5/8"	530	424	275	212	148	254	785	381	848
16	21/32"	497	397	258	198	139	238	736	366	795
17	11/16"	468	374	243	187	131	224	692	337	748
18		442	353	229	176	123	212	654	318	707
19	3/4"	418	335	217	167	117	201	619	301	670
20	25/32"	397	318	206	159	111	190	588	286	636
21	13/16"	378	303	197	151	106	181	560	272	606
22	7/8"	361	289	188	144	101	173	535	260	578
23	59/64"	345	276	179	138	96	166	512	249	553
24	15/16"	331	265	172	132	92	159	490	238	530
25	1"	318	254	165	127	89	152	471	229	509
26		306	244	159	122	85	146	452	220	489
27	1-1/16"	294	235	153	117	82	141	436	212	471
28	1-1/8"	284	227	147	113	79	136	420	204	454
29		274	219	142	109	76	131	406	197	439
30	1-3/16"	265	212	137	106	74	127	392	190	424
31		256	205	133	102	71	123	379	184	410
32	1-1/4"	248	198	129	99	69	119	368	179	397
33	1-5/16"	241	192	125	96	67	115	356	173	385
34		234	187	121	93	65	112	346	168	374
35	1-3/8"	227	181	118	90	63	109	336	163	363
36		221	176	114	88	61	106	327	159	353
37	1-7/16"	215	172	111	86	60	103	318	154	344
38	1-1/2"	209	167	108	83	58	100	309	150	335
39		204	163	106	81	57	97	301	146	326
40	1-9/16"	198	159	103	79	55	95	294	143	318
41	1-5/8"	194	155	100	77	54	93	287	139	310
42		189	151	98	75	53	90	280	136	303
43	1-11/16"	185	148	96	74	51	88	273	133	296
44	1-3/4"	180	144	94	72	50	86	267	130	289
45		176	141	91	70	49	84	261	127	282
46	1-13/16"	172	138	89	69	48	83	256	124	276
47		169	135	88	67	47	81	250	121	270
48	1-7/8"	165	132	86	66	46	79	245	119	265
49	1-15/16"	162	129	84	64	45	77	240	116	259
50		159	127	82	63	44	76	235	114	254
51	2"	156	124	81	62	43	74	230	112	249
52	2-1/16"	153	122	79	61	42	73	226	110	244
53		150	120	78	60	42	72	222	108	240
54	2-1/8"	147	117	76	58	41	70	218	106	235
55		144	115	75	57	40	69	214	104	231
56	2-3/16"	142	113	73	56	39	68	210	102	227
57	2-1/4"	139	111	72	55	39	67	206	100	223
58		137	109	71	54	38	65	203	98	219
59	2-5/16"	134	107	70	53	37	64	199	97	215
60	2-3/8"	132	106	68	53	37	63	196	95	212
61		130	104	67	52	36	62	193	93	208
62	2-7/16"	128	102	66	51	35	61	189	92	205
63		126	101	65	50	35	60	186	90	202
64	2-1/2"	124	99	64	49	34	59	184	89	198
65	2-9/16"	122	97	63	48	34	58	181	88	195



Anbefalt turtall ved bruk av HSS bor